



GreenFields Slide Max Pro

60 135 13.2

TECHNICAL DATA

RE1T1310631356003GP

Type	5/8" tufted sand/rubber filled synthetic grass carpet, straight stitch pattern
Pile content	100% polyethylene monofilament, diamond shape, U.V.-resistant, 13.200/6 dTex, 365 microns
Primary backing	Double 100% PP Thiobac, black, U.V.- stabilized, weight ca. 252 gr/m ²
Secondary backing	Latex compound with a base of styrene-butadiene (SBR), with drainage holes
Pile height	± 60 mm
Total thickness	± 62 mm
Stitch rate per 10 cm (width)	± 6,3
Stitch rate per 10 cm (length)	± 13,5
Number of tufts/m ²	± 8.505
Face weight	± 1.541 gr/m ²
Weight primary backing	± 252 gr/m ²
Weight secondary backing	± 1.000 gr/m ²
Total weight	± 2.793 gr/m ²
Roll width	410 cm
Roll length	as required
Tuft bind	≥ 30 Newton
Water permeability	± 60 ltr/m ² /min (unfilled)
Color Fastness	Xenon test : blue-scale>7, grey-scale>4

Version 1.1, 04-12-2017

COLOUR

Duo tone (Field green/Lime green), White and yellow for line marking.

Clarification numeric title code:

60 135 15.6 (example)

- first 2 digits : - second 3 digits*: - third 3 digits*:
 - pile height (mm) - stitches per meter - (x 1000) dTex

* if applicable



All data shown are typical values based on tests believed to be reliable by TenCate. All technical data provided herein are subject to change without prior notification. TenCate assumes no obligation or liability for the information in this document. No express warranties are given except for any applicable written warranties specifically provided by TenCate. All implied warranties including those of merchantability and fitness for a particular purpose are expressly excluded.



GreenFields Slide Max Pro

60 135 13.2

AVAILABLE SYSTEMS

System name	Performance Infill	Stabilizing Infill	Pad / E-layer / Geo	Tested
GreenFields Slide Max Pro 60 135 13.2 s sbr	SBR 32mm 16kg/m ²	Sand 8mm 10kg/m ²	--	A B
GreenFields Slide Max Pro 60 135 13.2 s sbr EL20	SBR 20mm 12kg/m ²	Sand 20mm 30kg/m ²	EL20	A B C
GreenFields Slide Max Pro 60 135 13.2 s sbr PE16.3011	SBR 20mm 11kg/m ²	Sand 23mm 34,5kg/m ²	NUT 3011-16	
GreenFields Slide Max Pro 60 135 13.2 s sbr PE12.7	SBR 23mm 12,7kg/m ²	Sand 22mm 33kg/m ²	HP XC 070 012	
GreenFields Slide Max Pro 60 135 13.2 s sbr PE12.9	SBR 23mm 12,7kg/m ²	Sand 22mm 33kg/m ²	HP XC 090 012	

Version 1.1, 04-12-2017

Symbols Explained

- A** FIFA Quality Programme for Football Turf, Handbook of Requirements October 2015 Edition (Quality)
- B** FIFA Quality Programme for Football Turf, Handbook of Requirements October 2015 Edition (Quality Pro)
- C** The International Rugby Board : Regulation 22, standard relating to the use of artificial playing surfaces.
- D** The GAA's "Performance and construction requirements for synthetic turf pitches (2009 edition)"
- E** The International Hockey Federation (FIH) "Handbook of performance requirements for synthetic turf hockey pitches"

All data shown are typical values based on tests believed to be reliable by TenCate. All technical data provided herein are subject to change without prior notification. TenCate assumes no obligation or liability for the information in this document. No express warranties are given except for any applicable written warranties specifically provided by TenCate. All implied warranties including those of merchantability and fitness for a particular purpose are expressly excluded.